



Spiral-Wound Gasket

GS-AB (Anti-Buckling) Product Range

Description:

3S SWG gaskets are wound with a “V” section profiled metal strip along with a soft filler material. The “V” section metal strip ensures the gasket has excellent compressibility and recovery under various applications. The soft filler material ensures sealability against the flange face, offering optimum performance.

GS-AB gaskets are designed to reduce inward buckling of the inner winding towards the bore of the pipe.

Style GS-AB comprises of the metal wire with designated filler. The outside diameter of the guide ring promotes the correct centering of the gasket on the flange face.

The notched inner diameter of the outer ring helps reduce inward buckling of the sealing element towards the bore of the pipe.



Maximum Temperature (Filler)	
3S Inhibited Graphite	850°F (454°C)
APX2® Graphite	975°F (524°C)
PTFE	500°F (260°C)
Mica	1800°F (982°C)
Mica/APX2®/Mica (HTG)	Min -238°F (-150°C) Max 1500°F (815°C)
Ceramic	2000°F (1093°C)
Maximum Temperature (Alloys)	
304 / 304L SS	1400°F (760°C)
316 SS	1400°F (760°C)
316L SS	1400°F (760°C)
321 SS	1500°F (815°C)
347 SS	1500°F (815°C)
Monel	1500°F (815°C)
Inconel 600	2000°F (1093°C)
Carbon Steel	900°F (482°C)